

Jet Gloss 90 /HTS320/65HG



Description

An 87 gram high gloss coated paper, laminated with a high tack permanent acrylic adhesive to a glassine liner.

Application

Jet Gloss 90 is a high gloss paper suitable for photorealistic printing. End uses include domestic and retail labelling where the visual quality of the product may be enhanced by the use of a high gloss coated label.

HTS320 is a modified aqueous emulsion acrylic designed to adhere well over a wide temperature range. Initial tack and ultimate adhesion are excellent to a variety of packaging substrates. This adhesive has been Isega approved for direct contact with dry, moist and fatty foods which have a reduction factor of at least 4.

65HG is a 60 gram honey glassine liner suitable for use where there is automatic label registration or dispensing.

Printing

This grade is used mainly for commercial inkjet printing, it is universally printable with dye and pigment inks. We recommend checking the suitability of this product on your individual printer before use.

Warranty

The above technical information, statements and recommendations are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All Smith & McLaurin products are warranted to be free of defects in material or workmanship for a period of one year from date of shipment. In no way will Smith & McLaurin be responsible for claims beyond the replacement value of the defective product or in any way liable or responsible for consequential or incidental damage.

All Smith & McLaurin products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. No express warranties and no implied warranties, whether of merchantability or fitness for any particular use, or otherwise, except as set forth above (which is made expressly in lieu of all other warranties) shall apply to products sold by Smith & McLaurin. Smith & McLaurin specifically disclaims and excludes all other such warranties. No waiver, alteration, addition or modification of the foregoing conditions shall be valid unless made in writing and signed by a director of Smith & McLaurin.

Face	Unit	Typical Value	Test Method
Substance	GSM	87 ± 5%	TAPPI 410
Caliper	Micron	100 ± 6%	TAPPI 411

Adhesive	Unit	Typical Value	Test Method
Peel Adhesion	N/25mm	18 to glass	FINAT 1
Loop Tack	N/25mm	10 to glass	FINAT 9
Service Temp	°C	-20 to 70 °C	----
Application Temp	°C	-10 °C	----

Backing Liner	Unit	Typical Value	Test Method
Substance	GSM	60 ± 5 %	TAPPI 410
Caliper	Micron	53 ± 7 %	TAPPI 411

