

# Jet Gloss Clear PP 80/AT231/65WG



## Description

An 80 micron high gloss transparent coated polypropylene film, laminated with a general purpose, all temperature, permanent acrylic adhesive to a glassine liner.

## Application

**Jet Gloss Clear PP 80** is a high quality transparent gloss coated film suitable for inkjet printing with water based inks. This film exhibits instant drying and good water and smudge resistance. End uses include domestic and retail labelling. End user testing is required to confirm suitability of all components in end use application.

**AT231** is an aqueous emulsion acrylic designed to adhere well over a wide temperature range. Initial tack and ultimate adhesion are excellent to a variety of packaging substrates. The adhesive has been Isega approved for direct contact with dry, moist and fatty foods which have a correction factor of at least 3.

**65WG** is a 62 gram white glassine liner suitable for use where there is automatic label registration or dispensing.

## Printing

This grade is used mainly for commercial inkjet printing, it is universally printable with pigmented and dye based inks. We recommend checking the suitability of this product on your individual printer before use.

To ensure a smudge free print and to maximise water resistance print with reduced ink saturation.

## Warranty

The above technical information, statements and recommendations are based upon tests believed to be reliable but do not constitute a guarantee or warranty. All Smith & McLaurin products are warranted to be free of defects in material or workmanship for a period of one year from date of shipment. In no way will Smith & McLaurin be responsible for claims beyond the replacement value of the defective product or in any way liable or responsible for consequential or incidental damage.

All Smith & McLaurin products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. No express warranties and no implied warranties, whether of merchantability or fitness for any particular use, or otherwise, except as set forth above (which is made expressly in lieu of all other warranties) shall apply to products sold by Smith & McLaurin. Smith & McLaurin specifically disclaims and excludes all other such warranties. No waiver, alteration, addition or modification of the foregoing conditions shall be valid unless made in writing and signed by a director of Smith & McLaurin.

Face	Unit	Typical Value	Test Method
Substance	GSM	80 ± 8%	TAPPI 410
Caliper	Micron	80 ± 8%	TAPPI 411

Adhesive	Unit	Typical Value	Test Method
Peel Adhesion	N/25mm	8 to glass	FINAT 1
Loop Tack	N/25mm	5 to glass	FINAT 9
Service Temp	°C	-20 to 70 °C	----
Application Temp	°C	-10 °C	----

Backing Liner	Unit	Typical Value	Test Method
Substance	GSM	62 ± 5 %	TAPPI 410
Caliper	Micron	53 ± 7 %	TAPPI 411

