

Technical Data Sheet

Ink-Jet Media specification Typical Values

NAK Gloss White PP Ink-Jet Label

Material code: PWC

Face Material characteristics:

Glossy Ink-Jet coated Polypropylene-Film (PP) with good absorption characteristics, vibrant color print-out on dye based and some pigmented inks. Test printouts recommended.

Parameter	Value	Unit	Standard
Basic weight	74 ± 5	g/m2	ISO 536
Paper thickness	89 ± 5	µm	ISO 534
Opacity	80 ± 5	%	ISO 2471
Stiffness md	19 ± 3	mN	ISO 2493
Stiffness cd	29 ± 1	mN	ISO 2493

Adhesive characteristics:

This adhesive is a permanent adhesive, high adhesion, universal useable,

Parameter	Value	Unit	test method
	from / to		
Temperature range:	-20°C	+80°C	climate Chamber / Kofler bank
Labelling temperature	min.	+5°C	on glass

Backing characteristics:

Kraft liner white

Parameter	Value	Unit	Standard
Basic weight	62 ± 6	g/m2	ISO 536
Paper thickness	51 ± 5	µm	ISO 534

Testing beforehand is always recommended.

All data to be considered as typical values and subject to change without prior notice.

For any inquiry or comment, please contact us via e-mail to salesupport@nakagawa.de

Rev.053117