

# UPM Raflatac Technical Information

08.10.2018 ENG 4580

<b>Product</b>		<b>PP INKJET M W ON-DEMAND / RPAF / WHITE GLASSINE 65</b>		
Sales Code	GFS/RPAF/01			
EAN	6415788276938			
Product use	Designed for multicolour inkjet printing. Specially developed for on-demand industrial applications. Pre-test recommended when label exposure to moisture conditions.			
<b>Face</b>		<b>PP INKJET MATT WHITE ON-DEMAND</b>		
Product	Matt finish coated white polypropylene.			
Substance	73	g/m <sup>2</sup>	ISO 536	
Caliper	105	µm	ISO 534	
Opacity	92	%	ISO 2471	
Printability	Inkjet printing, suitable for dye-and/or pigmented based inks: for new pigmented inks generation pre-testing is recommended. Ink-jet coating has been specially designed for the purpose, and the characteristics of these coatings might compromise the print result when using conventional methods such as flexography and offset.			
<b>Adhesive</b>		<b>RPAF</b>		
Type	General purpose permanent adhesive for A4 and cut-size applications.			
Composition	Acrylic, water borne.			
Tack min	9	N/25mm	FTM 9	
Labelling temperature min	5	°C		
Service temperature min	-20	°C		
Service temperature max	100	°C		
<b>Backing</b>		<b>WHITE GLASSINE 65</b>		
Product	White glassine, transparent backing paper.			
Substance	62	g/m <sup>2</sup>	ISO 536	
Caliper	55	µm	ISO 534	
Tensile strength MD	6.7	kN/m	ISO 1924	
Tensile strength CD	2.5	kN/m	ISO 1924	
Transparency	50	%	DIN 53147	
<b>Performance</b>				
Shelf life	From the date of manufacture: 2 years at +20 °C and RH 50%. Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.			
<b>Approvals</b>				
Approvals & Certifications	For food labeling applications, please consult your UPM Raflatac contact for the individual Declaration of Conformance (DoC) document of each product component for further compliance information.			



**Disclaimer**

The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

